



SP0092 Brilliant White

SP0096 Raven Black

SP0092 Brilliant White and SP0096 Raven Black are ready mixed 2K gloss topcoats for the car refinish market. They combine effortless application with fast drying properties and excellent gloss.

These topcoats provide superior coverage in 1-2 coats utilising the Spralac MS or HS Hardener range.

Key Features

- High gloss finish
- Outstanding coverage
- Very good gloss retention
- Medium and fast hardener options
- Excellent force drying properties
- Suitable for car refinish, utility vehicles and fleet

Product Details

Code	Product Name	Pack Size
800193	Spralac SP0092 Brilliant White	4L
800194	Spralac SP0096 Raven Black	4L
800097	Spralac SP2465 MS Hardener Fast	1L
800118	Spralac SP2445 MS Hardener Medium	1L
800096	Spralac SP2760 HS Hardener Fast	1L
800116	Spralac SP2750 HS Hardener Medium	1L
800111	SP3199	20L
800075	Spralac Thinner	5L
800070	Medium	1L

User Information



SP2445 SP2465
SP2750 SP2760

2:1 with +10-15% SP3199 Thinner Medium
Cure with Spralac MS or HS Hardeners



10-15 min 20°C

Flash off for 10-15 minutes between coats prior to baking



20-40 min 60°C
Pot Life
5 hours 25°C

Dry to handle in 20-40 minutes force dry at 60°C or 6-12hrs hours air dry at 25°C

Potlife is 20 min - 5 hours at 20°C



17-20 sec
DIN 4 20°C

Spray viscosity is 17-20 seconds, DIN 4 cup at 20°C



1.3-1.4mm
2 bar HVLP
2 coats, 40-60µm

Coating may be applied by HVLP 1.3-1.4mm / 2 bar. Typical application is 2 coats - 40-60 microns DFT



*SEE TECH. INFO

For more information, always refer to the latest version of the technical data sheet available at www.spralac.com

For more information on the Spralac range contact your local distributor or visit www.spralac.com